



2137 Hubbard Cres  
Ottawa ON,  
Canada  
K1J 6L3

## FuseFX™ Water Soluble Matting powder

**FuseFX WS-Series Matting Powder** is a unique blend of water base matting agents designed to eliminate the shine off of silicone painted surfaces, giving it a flat matt finish with little to no sheen.

**FuseFX WS-Series Matting Powders** must be used with **M/F-110 Clear** and both should be catalyzed together for best results.

**FuseFX WS-Series Matting Powders contains NO Amorphous Silica and NO Cabosil.** Please use an appropriate dust mask when using this product.

### ***How to use:***

After completing the final coat, touch-ups or airbrushed painting, mix equal amounts of Part A and Part B of **M/F-110 Clear**. Apply a thin coat of **M/F-110 Clear** to the piece and let cure or force dry with a hair dryer. Apply a second coat of **M/F-110 Clear**, this time very lightly, just enough to “wet” the surface. Go over the surface with a “dry” brush to pick up any extra blobs of paint making the surface even. The surface must be just moist otherwise it will leave little specks of white powder. In this case you can touch it up the white spots by carefully scrapping off or touching up with a little color.

While the **M/F-110 Clear** is still wet, loosely apply the **FuseFX Matting Powder** by sprinkling or using a dry “fluff” brush stippling the surface as you go, do not rub. A small Make-up Artist “Blush Brush” works great. You don’t have to apply lots of powder just a little stippling to cover the surface. *A little goes a long way.*

Once the surface is fully covered, use a hair dryer to force catalyzed the Clear and Powder together for **MINIMUM of 3 to 5 minutes** or let cure for about 3 hours. You may also place the powdered piece *IN A WARM OVER ONLY*. Too hot may cause the powder to crystallize, creating an uneven surface.

Once cured, you can wash the prosthesis under warm to hot water and a little soap, pat dry and the surface is now ready.

If you missed any spots, simply apply a thin coat of **M/F-110 Clear** to the shiny areas and add a little **FuseFX Matting Powder**.

Again, use a hair dryer to force cure the clear and powder together for **MINIMUM of 3 to 5 minutes**.

Once cured, you can wash the prosthesis under warm water and a little soap and pat dry.

If you find that the surface is too matt, you can always add a little sheen back to your already matt surface by stippling a very light thin coat **of M/F-110 Clear**.